

Adhesives

	Colour	Hardness	Resin Density, g/cc	Hardener Density, g/cc	Resin Viscosity @ 25°C, cps	Hardener Viscosity @ 25°C, cps	Viscosity Mixed at 25°C, cps	Mix Ratio by Weight	Mix Ratio by Volume	Gel Time @ 25°C, 150g mass, min.	Tack Free @ 25°C	978	600	MB002
551 Epoxy	Amber	88	1.15	0.99	3800	70	1800	100A : 18B	6A : 1B	30 - 35	PCR	✓	✓	✓
560 Epoxy A: B/C/D	White	75	1.26		semi-thixotropic		thixotropic				PCR	✓	✓	✓
560 B Fast	Red			1.03		70		100A : 18B		35 – 45		✓	✓	✓
560 C Medium	Yellow			0.96		50		100A : 12C		80 – 90		✓	✓	✓
560C	Orange					50		100A : 12C		25 - 35		✓	✓	✓
560 D Slow	Blue			1.02		55		100A : 16D		120 - 150		✓	✓	✓

The test data and results set forth herein are based on laboratory work and do not necessarily indicate the results that the buyer or user will attain. Base Group makes no warranty expressed or implied, including warranties of merchantability or fitness for a particular use. Under no circumstances will Base Group be liable for incidental, consequential or other damages, alleged negligence, breach of warranty, strict liability, tort or any other legal theory arising out of the use or handling of this product.

Base Group
 Ashville Way, Whetstone, Leicestershire LE8 6NU, UK
 Tel: +44 116 286 5073
 Fax: +44 116 275 3128
 Email: info@base-group.co.uk

www.base-group.co.uk



Base Group
Ashville Way, Whetstone, Leicestershire LE8 6NU, UK
Tel: +44 116 286 5073
Fax: +44 116 275 3128
Email: info@base-group.co.uk

www.base-group.co.uk