



www.RylardBoats.com

Technical Data Sheet

PRODUCT NAME: FIBREGLASS PRIMER

CODE NUMBER: A 5166

PRODUCT DESCRIPTION: A specially formulated primer for application to polyester glass fibre, to provide adhesion to the surface and allow for additional finishing operations.

PERFORMANCE/USE: Formulated as part of the Rylard range, the primer is designed for overcoating with Rylard undercoat and plus enamels. Gives excellent adhesion to this difficult surface.

SURFACE PREPARATION: The surface to be coated should be well rubbed down with 360 wet or dry paper and all traces of wax, parting agent and dirt removed. Degrease with a suitable degreasing solution immediately before applying primer.

APPLICATION: Suitable for application by brush or spray. Use as supplied.
Minimum application temperature: 10°C
Refer to our painting hints booklet before starting work.

DRYING/OVERCOATING:

Touch/Dust dry(15°C)	20-40 minutes
Hard dry/Overcoating(15°C)	16-24 hours

PHYSICAL PROPERTIES:

Supply Viscosity	33-36 seconds/ISO 6 cup/23°C
Supply SG	1.370
Colour	grey-green
Gloss Level	matt; primer
Theoretical Coverage:	8 square metres per litre per coat
VOC Content:	476 grammes per litre
Flash Point / Class / UN No	≥32°C & ≤55°C / III / UN 1263
Pack Size	750ml containers
Shelf Life	12 months unopened, stored at UK ambient temperatures.
Health & safety:	Refer to Product Safety Data Sheet before use.

This information is given in good faith for the guidance of users, but is without warranty or liability. Any queries should be referred to our technical department,

Distributed by:
Mainline
2 Sefton Road
Litherland
Liverpool L21 7PG
Tel: 0151 920 6451
Fax: 0151 920 6452

Your Local Stockist: